


### H cores



#### CORE SETS

#### CORE DIMENSIONS (mm)

Spray paint	Dimensions (mm)		
	$\Phi A$	$\Phi B$	C
Uncoat	$6.0 \pm 0.3$	$3.0 \pm 0.3$	$3.0 \pm 0.3$
Coat	6.8max	2.2min	3.8max

#### Effective core parameters

SYMBOL	PARAMETER	VALUE	UNIT
Ve	effective volume	56.50	mm <sup>3</sup>
le	effective length	13.10	mm
Ae	effective area	4.32	mm <sup>2</sup>
Wt	mass of core set	≈0.33	g

#### Characteristic

Grade	AL (nH/N <sup>2</sup> )	Z (Ω)
		f=1kHz U=0.25V N=10Ts, $\Phi 0.35$ mm
DN85H	310±25%	15 min